

# Industrial High Performance Bonding

Product Information Bulletin : **XHA 6660**

Spec # 57312

Industrial Foam Tape

**XHA™ 6660**



## Specialty Tape Division

250 Chester Street  
Painesville, Ohio 44077

Phone: **866-GO-AVERY (866-462-8379)**

Fax: **888-358-4469**

email: [psa.tape@averydennison.com](mailto:psa.tape@averydennison.com)

URL: [stus.averydennison.com](http://stus.averydennison.com)

### Surface Preparation

It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied be clean, dry, and free of grease or oil.

### Temperatures

Min Application Temp **50° F** **10° C**

Max Continuous Operating Temp **400° F** **204° C**

Max Intermittent Operating Temp **480° F** **249° C**

### Storage and Shelf Life

One year when stored at 70°F (21°C) 50% RH out of direct sunlight.

### Limited Warranty

All statements, technical information and recommendations concerning products sold or samples provided by AVERY DENNISON are based upon tests believed to be reliable but do not constitute a guarantee or warranty. All products are sold and samples of products provided with the understanding that PURCHASER has independently determined the suitability of such products for its purposes. AVERY DENNISON warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year\* after the initial date of shipment, AVERY DENNISON shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with AVERY DENNISON's standards, correct such defects by suitable repair or replacement without charge at AVERY DENNISON's plant or at the location of the products (at AVERY DENNISON's election) provided, however, if AVERY DENNISON determines that the repair or replacement is not commercially practical, AVERY DENNISON shall issue credit in favor of PURCHASER in an amount not to exceed the purchase price of the products.

This warranty is exclusive and is in lieu of any implied warranty of merchantability, fitness for a particular purpose or other warranty of quality, whether express or implied, except the warranty of title and against patent infringement. No waiver, alteration, additions or modifications of the foregoing conditions shall be valid unless made in writing and manually signed by an officer of Avery Dennison. \*Or in the time period stated on the specific product specification sheet, if any, and if not then on the specific product information literature in effect at time of shipment.

### Limitation of Liability

In no event shall AVERY DENNISON be liable for any incidental or consequential damages, including but not limited to, loss of profit, loss of use of production or loss of capital. The remedies of PURCHASER set forth herein are exclusive and the total liability of AVERY DENNISON with respect to any contract, or anything done in connection therewith such as the performance or breach hereof, or from the manufacture, sale, delivery, resale, installation or use of products whether arising out of contract, negligence, strict tort, or under any warranty, or otherwise, shall not exceed the purchase price of the products upon which the liability is based.

## PRODUCT DESCRIPTION

### Applications

XHA™ 6660 is particularly suited for superior adhesion to common substrates found in industrial applications. The conformable acrylic core allows for good stress relaxation and the adhesive bonds well to metals and painted surfaces.

| FEATURE                    | BENEFIT   |
|----------------------------|---|
| Visco-elastic acrylic foam | Very high adhesion combined with good shear and stress relaxation   |
| High density acrylic foam  | High density foam offers high temperature resistance                |
| Polyethylene liner         | Polyethylene liner combines moisture stability with tear resistance |
| Easy liner release         | Easy liner release enable smooth removal during application         |
| UV and solvent resistant   | Delivers long-term durability                                       |

## PRODUCT DATA

### Product Construction

| Tape               | Test Methods: PSTC-33 |             |
|--------------------|-----------------------|-------------|
|                    | US Mils               | MM's        |
| Acrylic Foam       | <b>23.5</b>           | <b>0.60</b> |
| Polyethylene       | <b>4.0</b>            | <b>0.10</b> |
| Total Construction | <b>27.5</b>           | <b>0.70</b> |

### Adhesive Properties

#### Peel Adhesion

Test Method(s): PSTC-3, ASTM D-3330, STD-10

| Substrate | Lbf / in  | US Oz / in | N / Meter    |
|-----------|-----------|------------|--------------|
| SS        | <b>17</b> | <b>272</b> | <b>2,977</b> |
| Aluminum  | <b>19</b> | <b>304</b> | <b>3,327</b> |

#### Dynamic Shear

Test Method(s): ASTM D-1002, STD-27

| Substrate | Lbf / Sq in | US Oz / Sq in | kPa        |
|-----------|-------------|---------------|------------|
| SS        | <b>110</b>  | <b>1,760</b>  | <b>758</b> |
| Aluminum  | <b>110</b>  | <b>1,760</b>  | <b>758</b> |

#### SAFT

Test Method(s): PSTC-5, ASTM D 3654, STD-243

| Substrate | Fail Temp °F |
|-----------|--------------|
| SS        | <b>400+</b>  |

THE LISTED VALUES ARE TYPICAL AND NOT INTENDED TO SERVE AS PRODUCT SPECIFICATIONS